

# I.W. Tremont Co., Inc.

Filter & Technical Specialty Papers

79 Fourth Avenue - Hawthorne, New Jersey 07506

Tel: 973-427-3800

Fax: 973-427-3778

www.iwtremont.com

## Technical Data Sheet

Material Designation

LL-95

Material Properties  
Summary

Binderless     Organic Binder     Double Laminated  
 Acrylic Binder     Laminated     Hydrophobic

This product is a very high efficiency multipurpose filter material with good heat resistance. This medium is effective for both gas and liquid filtration applications.

The base material consists of glass microfibers with 3-7% acrylic resin binder. The supporting scrim is a 0.5 oz/yd<sup>2</sup> Reemay, a high strength spun bonded polyester nonwoven.

The scrims are bonded to the glass media using a polyester hot melt which has a melting point of 325 degrees F.

### Micron rating

1

$\mu\text{m}$

### Basis Weight

81

lbs/3,000 ft<sup>2</sup>  
TAPPI Method T410

### Caliper Thickness

0.018

inches - 4 psi  
TAPPI Method T411

### Mean Pore Size

2.1

$\mu\text{m}$

### DOP Smoke Penetration

0.000

% at 0.3  $\mu\text{m}$  @  
10.5 ft/minute

ASTM Method D-2986

### Air Flow Resistance

54

mm H<sub>2</sub>O @  
10.5 ft/minute

ASTM Method D-2986

### Tensile Strength MD

6.0

lbs / inches  
TAPPI Method T494

### Tensile Strength CD

-

lbs / inches  
TAPPI Method T494

### Dry Elongation MD

-

%

TAPPI Method T494

### Dry Elongation CD

-

%

TAPPI Method T494

### Frazier Permeability

-

ft<sup>3</sup> / min / ft<sup>2</sup> @  
0.5in H<sub>2</sub>O W.G.

ASTM Method F778-82

### Gurley Stiffness

-

mg

TAPPI Method T543

### Water Repellency

-

Inches H<sub>2</sub>O

### Ignition Loss

-

% Loss

Comments:

Actual filtration performance, i.e. efficiency and dust holding capacity, will vary depending upon filter design parameters and the normal variation of the media properties consistent with the specification range. We continuously strive to define our products and hence the specifications are subject to change.