

### Technical Data Sheet

Material Designation

**D-48**

Material Properties  
Summary

- Binderless*     *Organic Binder*     *Double Laminated*  
 *Acrylic Binder*     *Laminated*     *Hydrophobic*

This is an intermediate efficiency filtration medium. It is composed of borosilicate glass microfibers with an acrylic binder. It is designed to be processed in either conventional or minipleat applications.

#### Micron rating

n/a

$\mu\text{m}$

#### Basis Weight

85

*lbs/3,000 ft<sup>2</sup>*  
TAPPI Method T410

#### Caliper Thickness

0.027

*inches - 4 psi*  
TAPPI Method T411

#### Mean Pore Size

n/a

$\mu\text{m}$

#### DOP Smoke Penetration

0.25

*% at 0.3  $\mu\text{m}$  @  
10.5 ft/minute*

ASTM Method D-2986

#### Air Flow Resistance

26.0

*mm H<sub>2</sub>O @  
10.5 ft/minute*  
ASTM Method D-2986

#### Tensile Strength MD

5.0

*lbs / inches*  
TAPPI Method T494

#### Tensile Strength CD

4.0

*lbs / inches*  
TAPPI Method T494

#### Dry Elongation MD

1.0 - 1.5

%

TAPPI Method T494

#### Dry Elongation CD

1.5 - 2.0

%

TAPPI Method T494

#### Frazier Permeability

n/a

*ft<sup>3</sup> / min / ft<sup>2</sup> @  
0.5in H<sub>2</sub>O W.G.*

ASTM Method F778-82

#### Gurley Stiffness

n/a

*mg*

TAPPI Method T543

#### Water Repellency

n/a

*Inches H<sub>2</sub>O*

#### Ignition Loss

5.0 - 8.0 max.

*% Loss*

**Comments:** Rev to caliper thickness 031414. Prior ver stated 0.012inch.

Actual filtration performance, i.e. efficiency and dust holding capacity, will vary depending upon filter design parameters and the normal variation of the media properties consistent with the specification range. We continuously strive to define our products and hence the specifications are subject to change.